



Number #: 215-53C

Name: Pressed Eyeshadow Trio

Category: Color of the Year

Date: 01/05/2022

No	Phase	Trade Name	INCI	%
1	A	SanTalc AV	Talc, Aloe Barbadensis Leaf Extract	17.48
2	A	SanMica AV	Mica, Aloe Barbadensis Leaf Extract	14.46
3	A	Biluna 2600 UVS	Bismuth Oxychloride, Magnesium Stearate, PEG-10 Dimethicone	4.80
4	A	Micropoly 250S	Polyethylene	3.60
5	A	Zinc Stearate	Zinc Stearate	3.60
6	A	Aerosil R972	Fumed Silica	0.06
7	B	Marvel Antique Purple	Mica, TiO2, Tin Oxide, Black2	35.00
8	B	Fantasy Purple	Titanium Dioxide, Mica, Ferric Ferrocyanide, Tin Oxide, Tripropylene Glycol Diacrylate, AL Powder	9.00
9	C	Vitamin E	Tocopheryl Acetate	0.75
10	C	NOO Crystal	Octyldodecyl Oleate, Tocopheryl Acetate	4.50
11	C	Beeswax SP-422P	Beeswax	0.15
12	C	Wickenol 171	Ethylhexyl hydroxystearate	4.50
13	C	Jeecide Phenoxy	Phenoxyethanol	1.50
14	C	Propyl Paraben	Propyl Paraben	0.15
15	C	Methyl Paraben	Methyl Paraben	0.45
<b>Total</b>				<b>100%</b>
<b>Procedure</b>	Premix Phase A in osterizer blender and mix thoroughly until well blended. Add phase B to A and gently mix for 1 minute. Preweigh phase C into glass beaker and heat to 70°C and stir until all is dissolved and uniform. Add phase C to A and B and blend for one minute. Scrape down sides and repeat blending process. Press into desired eyeshadow pans. Press at 750 psi, 3 seconds for 215-53C			

The information provided is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Sandream Specialties LLC. Customers should utilize formulations provided as a guide and perform in-house stability, micro and other necessary testing.